

## Tabla de Durezas

Brinell	Vickers	Rockwell "E"	Rockwell "C"	Brinell	Vickers	Rockwell "E"	Rockwell "C"
HB	HV	Hre	Hrc	HB	HV	Hre	Hrc
118	125	68.5	-	269	284	-	27.6
121	127	70.0	-	275	292	-	28.7
122	130	71.0	-	285	301	-	29.9
126	132	72.0	-	295	310	-	31.0
128	135	73.0	-	302	319	-	32.1
131	137	74.0	-	312	329	-	33.2
134	140	75.0	-	321	339	-	34.3
137	143	76.5	-	331	350	-	35.4
140	147	77.5	-	341	360	-	36.6
143	150	78.5	-	352	372	-	37.8
146	153	79.5	-	363	383	-	39.1
149	156	81.0	-	375	396	-	40.4
152	159	82.0	-	388	410	-	41.8
156	163	83.0	-	402	425	-	43.1
159	167	84.0	-	415	440	-	44.5
163	171	85.0	-	430	457	-	45.8
166	175	86.0	-	444	474	-	47.2
170	178	87.0	-	-	495	-	48.7
175	183	88.0	-	-	516	-	50.3
179	188	89.0	-	-	535	-	51.4
183	192	90.0	-	-	553	-	52.5
187	196	90.5	-	-	560	-	53.0
192	202	91.5	-	-	577	-	54.0
197	207	93.0	-	-	595	-	55.0
202	212	93.5	-	-	613	-	56.0
207	218	94.5	-	-	633	-	57.0
212	222	95.5	-	-	653	-	58.0
217	228	96.5	-	-	674	-	59.0
229	234	97.5	19.0	-	697	-	60.0
229	241	98.0	20.5	-	720	-	61.0
235	247	99.0	21.6	-	746	-	62.0
241	253	100.0	22.8	-	772	-	63.0
248	261	101.0	24.1	-	800	-	64.0
255	269	-	25.4	-	832	-	65.0
262	276	-	26.5	-	-	-	-